

Technical Data Sheet



ALBANY ALL PURPOSE PRIMER A versatile primer for many surfaces

AVAILABILITY

Colour Beige

Packaging 1 & 2.5 litre

PROPERTIES

Drying time Under normal drying conditions surface dry 6-8 hours and recoatable after 16 hours. Allow for adequate ventilation during the drying period.

Finish Not applicable

Composition Pigment: Titanium Dioxide, anti-corrosive pigments and extenders
Binder: Long Oil Alkyd
Solvent: Dearomatised White Spirit

Spreading rate up to 15m² per litre on smooth surfaces

Wet film thickness 71 micrometres at 15m² per litre

Dry film thickness 43 micrometres at 15m² per litre

Volume solids 61%

Flash point 40°C. (closed cup)

VOC content EU limit value for this product (cat.A/g): 350 g/l (2010)
This product contains max. 349 g/l VOC

Limitations Do not apply when air or substrate temperatures are likely to fall below 5°C or when the relative humidity is above 80% during application or the drying period.

PREPARATION

New surfaces

Timber

All surfaces must be suitably dry, and free from anything that will interfere with the adhesion of the materials to be applied. Rub down with a suitable grade of abrasive paper and round sharp edges 1-3mm. Remove all dust. Timber with oils/extractives must be swabbed with methylated spirits, Treat knots with two thin coats of fresh knotting. Fill any fixing holes, open joints and shallow surface defects with a suitable proprietary filler. Rub down with a suitable grade of abrasive paper.

All Metals

Including galvanised

Surfaces must be clean and free from anything that will interfere with the materials to be applied. Wash with hot water and liquid detergent solution to remove oil, grease or any other contaminants, frequently changing the water. Rinse thoroughly with clean water. Allow to dry. Galvanised surfaces should be pre-treated with a suitable mordant solution. Overall blackening of the surface will confirm satisfactory surface preparation.

Additional Surface

Preparation –

All metals

Non-ferrous Metals

Lightly abrade to a bright (not polished) surface – excluding galvanised surfaces. Rinse thoroughly with clean water to remove all residues. Allow to dry.

Ferrous Metals

Remove all millscale and rust back to clean metal. Remove all residues. Prime within the working day.

Previously Decorated Surfaces

Timber

All surfaces must be suitably dry, and free from anything that will interfere with the adhesion of the materials to be applied. Remove all loose, and failing or suspect paint. Remove grey and denatured surfaces by rubbing down with abrasive paper

Technical Data Sheet



or by mechanical means and round sharp edges 1-3mm. Feather edges of sound paint. Remove all dust. Organic growth must be removed and the areas treated with Albany Fungicidal Wash. Remove any defective putty glazing, clean and prime rebates, replacement putties must be allowed to form a hard skin. Treat knots with two thin coats of fresh knotting. Fill any fixing holes, open joints and shallow surface defects with a suitable proprietary filler or a two pack proprietary wood filler. Rub down with a suitable grade of abrasive paper. Remove all dust. Spot primer all bare and filled areas with one coat of Albany Primer.

Metals

All surfaces must be suitably dry, and free from anything that will interfere with the adhesion of the materials to be applied. Remove all loose, and failing or suspect paint. Feather edges of sound paint. Remove all dust. Remove all rust. Spot prime non-ferrous and ferrous metals with Albany All Purpose Primer.

Timbers and Metals

Wash remaining sound paint with hot water and liquid detergent solution to remove any contaminants, frequently changing the water. Wet abraded to provide a key. Rinse with clean water to remove all residues. Allow to dry. Bring forward spot primed areas as required with paint system to be used.

COATING SYSTEM

Apply one coat.

APPLICATION

Stir well before use. Apply by brush or roller in the direction of the grain. Prior to application, the moisture content of the substrate should not exceed 18%.

CLEANING

Return surplus material to container. Clean with a proprietary cleaner immediately after use.

MAINTENANCE INFORMATION FOR CDM FILE HEALTH AND SAFETY

Between maintenance redecoration surfaces may be washed with a warm water and liquid detergent solution to remove surface dirt.

Please refer to the Safety, Health and Environmental Information on the container. Take special precautions during the surface preparation of pre 1960s painted surfaces as they may contain harmful lead. For further information contact Brewers. When preparing all surfaces avoid the inhalation of dust and/or metal particles. Wear a suitable facemask. Material Safety Data Sheets for this and all other Albany products are freely available from the place of purchase or the address below. Store in secure dry conditions between 5°C and 40°C and inaccessible to children or animals. Containers should be kept closed during storage. Do not empty into drains, watercourses or access routes to septic tanks.

GENERAL INFORMATION

Apply all products in accordance with BS 6150: 2019 Code of practice for painting of buildings and BS 8000: Part 12: 1989 Code of practice for decorative wallcoverings and painting. Under normal and frost free conditions this product will remain usable for up to two years if stored correctly and unopened.

Every care is taken to ensure that all information provided on this Technical Data Sheet is accurate. Brewers are unable to guarantee results as it has no control over the conditions under which its products are applied.

Before using this product please ensure you have the latest information. For help or more information contact:

Brewers

Tel: 01323 411080

Email: enquiries@brewers.co.uk

Website: www.brewers.co.uk

This information is correct at date of issue September 2023.