



## DENSE PAINT GRADE

### Smooth Textured Paint Grade Blocks

The Dense Paint Grade finish provides a close-textured surface suitable for internal painted applications where appearance and consistency of texture of the painted wall is required. These blocks are not fair-faced or intended to be left unfinished as the consistency of shade and colour cannot be guaranteed.

All dense blocks are manufactured from high quality class 2 aggregates, including a significant proportion of recycled raw material and are suitable for use above and below damp-proof course (DPC).

Dense Paint Grade blocks are manufactured to BS EN 771-3 and are ISO 9001 Quality Assured, ISO 14001 Environmentally Certified and hold BES 6001 Responsible Sourcing certification.

### TECHNICAL PROPERTIES

Property	Value
Face Size (BS EN 771-3):	440mm x 215mm
Dimensional Tolerance (BS EN 772-16):	Category D1
Gross Dry Density (BS EN 772-13):	1850 - 2100 kg/m <sup>3</sup>
Mean Compressive Strength (BS EN 772-1):	10.4 N/mm <sup>2</sup>
Manufacturing Category (BS EN 771-3):	Category II
Thermal Conductivity (BS EN 1745):	1.17 W/mK [inner leaf] 1.26 W/mK [outer leaf]
Moisture Movement (BS EN 772-14):	< 0.6 mm/m
Fire Resistance (BS EN 13501-1):	Class A1 reaction to fire
Configuration (BS EN 1996-1-1):	Solid - Group 1
Available Texture, Finish:	Paint Grade



### APPLICATIONS

- Manufactured to BS EN 771-3.
- Inner & outer leaf of external cavity walls.
- Internal partition walls.
- Acoustic separating party walls to Part E of the Building Regulations and Robust Details.
- Close-textured finish for internal painted applications.
- Robust, accepts most standard fixings.
- Unsuitable for external or unfinished fair-faced applications.

### PHYSICAL PROPERTIES

Block Size mm	'R' Value m <sup>2</sup> k/W	Walled Weight kg/m <sup>2</sup> See Note 1	Sound Reduction Rw, dB See Note 2	Block Weight kg See Note 3	Fire Resistance Hours See Note 4
75	0.06	143	46	13.5	2
100	0.09	190	48	18.0	4
140	0.12	266	51	25.2	4

1. Walled weight is for a single-leaf wall, plastered on both sides.
2. Sound Reduction Rw values are based on wall mass and assumes a plastered finish on both sides.
3. The block weights quoted above are approximate and include the typical additional weight from the equilibrium (3%) moisture content of the block. Received block weights will be significantly higher and are variable due to moisture content.
4. Fire resistance periods to BS EN 1996-1-2 for a single-leaf, non-loadbearing plastered wall.

### PACK DETAILS

Block Size mm	Blocks per pack	m <sup>2</sup> per pack
75	96	9.6
100 (Void Pack)	72 (66)	7.2 (6.6)
140 (Void Pack)	48 (44)	4.8 (4.4)

Pack details may vary slightly between manufacturing locations. Always check details with your nearest sales office.

Thermal

The table below shows examples of how cavity walls built with a solid Dense Paint Grade block inner leaf can meet a range of u-value targets. For specific calculations, please contact our technical department.

U Value W/m²K	Partially Filled Cavity Brick outer leaf   50mm clear cavity   plasterboard on dabs	Fully Filled Cavity Brick outer leaf   Fully filled cavity   plasterboard on dabs
0.25	50mm PIR/PU @ 0.018 65mm PIR/PU @ 0.022	125mm batt @ 0.034
0.22	60mm PIR/PU @ 0.018 75mm PIR/PU @ 0.022	125mm batt @ 0.030
0.20	70mm PIR/PU @ 0.018 85mm PIR/PU @ 0.022	100mm batt @ 0.021
0.18	80mm PIR/PU @ 0.018 95mm PIR/PU @ 0.022	150mm batt @ 0.030
0.15	100mm PIR/PU @ 0.018 120mm PIR/PU @ 0.022	100mm batt @ 0.021 + 35mm insulated drylining

Note: Insulation thicknesses shown are the minimum required to meet the target u-value. These sizes may not be available, therefore the next size up should be used.

Acoustic

Dense Paint Grade blocks are suitable for use in acoustic separating party walls between dwellings and for internal partitions in accordance with Part E of the Building Regulations. They are also suitable for a range of Robust Standard Detail party walls. The figures below are predicted sound reduction ratings based on wall mass:

Block Thickness mm	Walled Weight kg/m²	Predicted Sound Reduction, Rw		
		Unfinished	Plastered	Dry Lined
75	143	44	46	45
100	190	47	48	48
140	266	50	51	51

Below Ground

All of our aggregate and dense concrete blocks are durable products which are suitable for use in soil conditions up to Design Sulphate class DS-3 as defined in BRE Special Digest 1. Dense Concrete blocks of any strength can be used below dpc.

Fire Resistance

Dense Paint Grade blocks are non-combustible with zero spread of flame and are classed as Class ‘A1’ in accordance with BS EN 13501-1. Notional fire resistance periods based on BS EN 1996-1-2 are:

Block mm	Loadbearing Wall		Non-loadbearing Wall	
	No Finish	VG Plaster	No Finish	VG Plaster
100	2 hours	4 hours	4 hours	4 hours
140	3 hours	4 hours	4 hours	4 hours

“VG” = vermiculite / gypsum plaster or perlite plaster 13mm thick applied to both faces of single leaf walls.

Mortars

Dense Paint Grade blocks offer a good surface for accepting mortars and no pretreatment is required other than ensuring that all dirt and debris is removed. Generally, in order to avoid unsightly cracking, the weakest mortar mixture appropriate to the structural requirements should be selected as per BS 5628-3. For most applications, we recommend that grade iii mortar is used.

	Mortar Class BS EN 1996-1-1	Recommended mix proportions of materials by volume (as per BS EN 998-2)	
Above dpc	(iii) M4	1 : 1 : 5½ to 6 1 : 5½ to 6 1 : 4½ to 5	Cement : Lime : Sand Cement : Sand (with plasticiser) Masonry Cement : Sand
Below dpc	(ii) M6	1 : ½ : 4 to 4½ 1 : 3½ to 4	Cement : Lime : Sand Cement : Sand

External Rendering

Dense Paint Grade blocks have a very smooth close-textured surface and are not recommended for external rendering. For this application our standard-texture Dense blocks are more suitable.

Suspended Block & Beam Floors

Solid Dense blocks of any strength are suitable for use as infill blocks in block and beam suspended floors and can be laid either 440mm wide or 215mm wide.

Wall Ties & Movement Joints

Generally under normal conditions, wall ties should be embedded 50mm into the mortar on each leaf, staggered in alternate courses and spaced in accordance with the following:

Leaf Thickness mm	Cavity Width mm	Horizontal Spacing mm	Vertical Spacing mm	Ties per m²
Less than 90mm	50 - 75	450	450	4.9
Over 90mm	50 - 150	900	450	2.5

For unreinforced masonry panels, the typical recommended spacing between vertical movement joints for Dense blocks is 7m - 9m for internal and external walls.

Good Site Practice & Safe Handling

- Packs should be stored on firm, level ground no more than 2 packs high and protected from severe weather to preserve their quality. Care must be taken when removing the plastic bands as individual blocks may fall out. Never un-band packs above shoulder height.
- In the absence of a revised version of the HSE guidance given in their withdrawn Construction Sheet 37 ' Handling Building Blocks' the following principles should be followed: There is a risk of injury in the repetitive handling of blocks heavier than 20kg. Repetitive manual handling of blocks over 20kg should be subject to a risk assessment and a safe system of work should be established before block-laying commences.
- Blocks should not be laid if the temperature is at or below 3°C and falling.
- Blocks should always be laid on a full bed of mortar and vertical joints filled.

NBS Clauses for our concrete block products can be found on [www.source.thenbs.com](http://www.source.thenbs.com)

June 2023



Product details and availability may vary between manufacturing locations. Please contact your nearest regional sales office for sales, product and technical advice.

North East Region :	Tel: 01207 544 214	Fax: 01207 541 800	blocks@thomasarmstrong.co.uk
Cumbria, North Lancashire and Borders Region :	Tel: 01900 68114	Fax: 01900 66136	cumbriablocksales@thomasarmstrong.co.uk
Yorkshire, Humber and Lincolnshire Region :	Tel: 0113 232 0022	Fax: 0113 287 0839	leedssales@thomasarmstrong.co.uk
North West, Cheshire, Staffordshire and West Midlands Region :	Tel: 0151 525 5991	Fax: 0151 530 1676	aintreesales@thomasarmstrong.co.uk