

Technical Data Sheet

ALBANY AF1 Ceiling Paint

Albany AF1 Ceiling Paint is a water-based coating for interior ceilings, containing matting agents to help hide imperfections as well as brush or roller marks, giving ceilings a consistent appearance.

AVAILABILITY

Colour Range	White
Packaging	10 Litre

PROPERTIES

Drying Time	Under normal drying conditions touch dry in 30 minutes and recoatable after 4 - 6 hours. Allow for adequate ventilation during the drying period, High humidity can extend the drying time.
Finish	Super Flat
Composition	Pigment: Titanium dioxide, extenders Binder: Styrene acrylic polymer Solvent: Water
Spreading Rate	9m ² per litre, depending upon surface texture, porosity and the method of application.
Volume solids	45%
VOC Content	EU limit value for this product (Cat A/a): 30g/l (2010). This product contains max 30 g/litre VOC. LOW VOC CONTENT 0.3-7.99%.
Flash Point	Non-flammable
Wet Film Thickness	110 micrometres at 9m ² per litre
Dry Film Thickness	46 micrometres at 9m ² per litre
Scrub Rating	Class 2
Limitations	For interior use only. Do not apply when air or substrate temperatures are likely to fall below 8°C or when the relative humidity is above 80% during application or the drying period.

PREPARATION

New Surfaces	For best results, surfaces must be clean, dry and free from grease or dust. All loose materials and defective paint must be removed, and the surface primed with a thinned coat of Albany AF1 Ceiling Paint up to 20%.
Previously Painted Surfaces	All surfaces must be clean, dry and free from grease or dust as well as any organic growth. All loose materials and defective paint must be removed, and the areas treated prior to painting. Fill any fixing holes, cracks, and shallow surface defects with a suitable filler. Prime bare and filled areas with thinned coat of Albany AF1 Ceiling Paint upto 20%. Wash remaining sound paint with warm soapy water to remove any contaminants. Glossy surfaces should be thoroughly abraded before application to ensure good adhesion. Rinse with clean water to remove all residues, allow to dry. If after cleaning any areas still contaminated with substances likely to cause staining and/or bleeding, treat with a suitable stain blocker prior to painting.

COATING SYSTEM	For best results apply 2 coats. (where priming is required apply 1 coat of Albany AF1 Ceiling Paint thinned upto 20% with clean water, followed by 2 standard coats).
----------------	---

APPLICATION	Stir well before use. Apply by brush, roller or spray.
-------------	--

CLEANING	Wash equipment immediately after use in warm soapy water and rinse thoroughly.
----------	--

ALBANY AF1 Ceiling Paint

HEALTH AND SAFETY Please refer to the Safety, Health and Environmental Information on the container. Take special precautions during the surface preparation of pre 1960's painted surfaces as they may contain harmful lead. For further information contact the Customer Relations Team. When preparing all surfaces avoid the inhalation of dust and/or metal particles. Wear a suitable facemask. Material Safety Data Sheets for this and all other Albany products are freely available from the place of purchase or the address below. Store in secure dry conditions between 5°C and 40°C and inaccessible to children or animals. Containers should be kept closed during storage. Do not empty into drains, watercourses or access routes to septic tanks.

**GENERAL
INFORMATION**

Apply all products in accordance with BS 6150: 2019 Code of practice for buildings and BS 8000: Part 12: 1989 Code of practice for decorative wallcoverings and painting. Under normal and frost free conditions this product will remain usable for up to two years if stored correctly and unopened. Every care is taken to ensure that all information provided on this Technical Data Sheet is accurate. C Brewer & Sons Ltd are unable to guarantee results as it has no control over the conditions under which its products are applied.

Before using this product please ensure you have the latest information.

For help or more information contact:

Brewers
Tel: 01323 411080
E-mail: enquiries@brewers.co.uk
Website: www.brewers.co.uk

This information is correct at date of issue February 2025