

Emulsified Bitumen/Rubber Latex Waterproofing Coating

An alkali resistant cold applied rubberised bitumen emulsion which has excellent adhesion to sound building materials including asphalt. It retains flexibility in low temperatures and is resistant to softening in warm conditions. ADOCOAT is used on walls and floors to prevent water ingress and dampness from the ground. It can be used to provide a flexible waterproof membrane on most building surfaces, and may be extended to produce flexible crack filler. It is brown in colour, on application and dries to black

Advantages

- Waterproof coating to bridge abutments
- Repairs to cracks in black top surfacing and concrete
- Waterproofing concrete surfacing & roofing
- Fixing woodblocks and panel parquetry
- Waterproofing retaining walls and can be used as a keying treatment
- Sandwiching damp proof membranes, under concrete and roof screeds
- Protects concrete structures against attack by sulphates present in soils
- Provides a key for plaster on difficult surfaces

Application

Preparation and Application Requirements

ADOCOAT should always be applied to surfaces which are clean and free from dust, oil and other surface contaminants. It should not be applied in temperatures below 5°C. Porous and hot dry surfaces should be dampened with clean cold water to assist the application of the product.

Stir well before use. Apply by brush. Do not apply to external surfaces in wet weather or if rain is threatened. Allow good ventilation in confined areas. In multi coat applications, each coat should be allowed to dry completely before the next coat is applied. Protect treated surfaces from frost until fully dried.

Waterproof Coating to Bridge Abutments, Structures and Foundations

Apply two coats, each at 2m² per litre (the 2nd at right angles to the first). When treating foundations, the coating should be taken to meet the damp proof course provided in the base or wall. ADOCOAT can be applied to green concrete surfaces immediately after the shuttering has been removed to act as a curing membrane. It is recommended that 48 hours be allowed to elapse before back-filling.

Repairs to Cracks in Blacktop Surfacing and Concrete

Fine cracks may be filled with neat ADOCOAT. Larger cracks up to approximately 6 mm are filled with a mixture of 2 volumes of ADOCOAT to 1 volume of fine sand. Cracks in excess of 6 mm should be filled with a similar mixture plus the addition of approximately 10% of Portland cement. Neat ADOCOAT may be poured into the crack, whilst filled mixtures are best applied with a pallet knife or similar. Repairs should be blinded with sand if early trafficking is intended. Larger repairs may need topping up after 24 hour treatments.

Waterproofing Exterior Walls

Remove all dirt, dust and grease. Uneven surfaces should be levelled using cement mortar. Bare brickwork should be covered with a thin skin of cement mortar, which should be allowed to dry. Apply 3 coats of ADOCOAT, each at 2m² per litre (each at right angles to the previous). The final coat should be blinded with sharp sand while it is still tacky.

NOT recommended for use on Interior walls below ground level with extreme dampness. Recommended to treat the exterior as ADOCOAT is unlikely to resist exposure to free water or water pressure (conditions often found in basements & cellars)

Floors

Sandwich Construction—severe conditions and heavy dampness. Apply 2 coats of ADOCOAT onto clean & smooth concrete sub floor at 1m² per litre. While the second coat is still tacky, blind with clean sand as a protection against foot traffic and to provide a good key for the top screed. It is important that ADOCOAT is taken up the walls to marry with the existing damp proof course and the dried film is not punctured or damaged. Apply the top screed at a thickness of 50mm minimum and allow to dry before laying a floor covering

Adocoat should never be left as the final surface for pedestrian traffic. It should always be covered by a suitable floor covering material

Cleaning

Tools should be cleaned immediately after use with warm clean water. If ADOCOAT has hardened RESOKLENS should be used to soften the material.

Coverage

Coverage is 1-2m² per litre per coat of undiluted material.

Drying time is 3 to 6 hours but this may be extended in humid or poorly ventilated situations.

Storage

The material should be stored in a closed container and protected from the frost.

Shelf Life

12 months in tightly sealed containers

Specification

ADOCOAT Emulsion is manufactured by Adomast Manufacturing Ltd and shall be applied strictly in accordance with the manufacturer's instructions. For specific advice regarding any aspect of this product, please consult our Technical Department

Health and Safety

Care should be taken to avoid splashes entering eyes. Contact with skin should be avoided and hands washed thoroughly in the event of accidental contact. ADOCOAT Emulsion should not be ingested. If splashes affect eyes, they should be bathed immediately with copious quantities of clean water and if discomfort persist medical attention should be sought without delay.

See separate Safety Data Sheet for further information.