

PRODUCT DATA SHEET



Portland Stone Firms Limited <i>99 Easton Street, , Portland, Dorset, DT5 1BP.</i>					
Broadcroft Whitbed					
ACS Testing Limited					
Address: Unit 14 Blackhill Road West, Holton Heath Trading Park, Poole, Dorset, BH16 6LE Tel 01202 622858 Fax 01202 625045					
ACS Test Ref.	Test Description (Test Method)	Result	Units	Date	
M71	Determination of resistance to salt crystallization (BS EN 12370:1999)	Mean Mass Change	-27.0	%	Apr 2012
M72	Determination of frost resistance (BS EN 12371:2010)	Change in Performance	-4.2	%	Feb 2012
M73	Determination of flexural strength under concentrated load (BS EN 12372:2006)	Flexural Strength R _{tf}	ND*	MPa	N/A
M73i	Frost Resistance - Determination of flexural strength under concentrated load (BS EN 12372:2006)	Flexural Strength R _{tf} (after Frost Cycles)	ND*	MPa	N/A
M74	Determination of petrographic examination (BS EN 12407:2007)	Limestone Oomicrite		Description	Jan 2012
M75	Determination of flexural strength under constant moment (BS EN 13161:2008)	Flexural Strength R _{tc}	7.2	MPa	Dec 2011
M75i	Frost Resistance - Determination of flexural strength under constant moment (BS EN 13161:2008)	Flexural Strength R _{tc} (after Frost Cycles)	6.9	MPa	Feb 2012
M76	Determination of breaking load at dowel hole (BS EN 13364:2002)	Mean Breaking Load	ND*	N	N/A
M77	Determination of water absorption at atmospheric pressure (BS EN 13755:2008)	Mean Water Absorption	6.4	%	Dec 2011
M78	Determination of abrasion resistance (BS EN 14157:2004)	Mean Groove Length	26.0	mm	Dec 2011
M79dry	Determination of slip resistance by pendulum tester (BS EN 14231:2003)	SRV "DRY" =	83	nr.	Dec 2011
M79wet	Determination of slip resistance by pendulum tester (BS EN 14231:2003)	SRV "WET" =	76	nr	Dec 2011
M80	Determination of water absorption coefficient by capillarity(BS EN 1925:1999)	Absorption Coefficient. (Perpendicular to plane of Anisotropy)	68.7	g/m ² .s ^{0.5}	Jan 2012
M80	Determination of water absorption coefficient by capillarity(BS EN 1925:1999)	Absorption Coefficient. (Parallel with plane of Anisotropy)	68.1	g/m ² .s ^{0.5}	Jan 2012
M81	Determination of uniaxial compressive strength (BS EN 1926:2006)	Compressive Strength R	49	MPa	Dec 2011
M82	Determination of real & apparent density, and total & open porosity (BS EN 1936:2006)	Real Density	2710	kg/m ³	Jan 2012
M82	Determination of real & apparent density, and total & open porosity (BS EN 1936:2006)	Apparent Density	2280	kg/m ³	Jan 2012
M82	Determination of real & apparent density, and total & open porosity (BS EN 1936:2006)	Open Porosity	15.5	%	Jan 2012
M82	Determination of real & apparent density, and total & open porosity (BS EN 1936:2006)	Total Porosity	15.6	%	Jan 2012
Notes: ND* = Not Determined/Requested	Approved :	91.	Date :	02/05/2012	
Approved Signatories : <input type="checkbox"/> S J White Head of Laboratories <input type="checkbox"/> A Bates Laboratory Manager <input type="checkbox"/> K Tiller Technical Manager <input checked="" type="checkbox"/> M Slater Senior Technician					