Forticrete[®] Regency Textured Ashlar



Forticrete's Cast Stone Regency Textured Ashlar Blocks have been developed to replicate a natural Ashlar Stone with a decorative treatment consisting of small grooves, better known as 'Mason's Drag'.

Buff

Features

- Available in all standard Ashlar sizes.
 Bespoke sizes available.
- The combed effect varies, replicating natural stone.
- All our standard colours are available, plus special colours on request.



Portland




Buff






Holyrood

Glamis Red Sherwood





The reproduction of colour is as close as is possible within the photographic and printed processes. Where precise colour tolerances are vital, you are advised to view actual product samples.



St Elphin's Park Retirement Village, Robinson Court, Darley Dale, Matlock, supplied using three colours of Regency Textured Ashlar.

Specification

The major technical performance characteristics of Forticrete Cast Stone Dressings exceed the requirements of BS EN 771-5:2011.

Normalised Compressive Strength	Category I, 25N/mm² (perpendicular to bed face) (BS EN 771-5:2011) In excess of 35N/mm² (BS 1217)
Gross Dry Density	Gross Dry Density: 2000kg/m ³
Thermal Conductivity	1.00 W/mK
Water absorption (typical)	<2g/m ² .s
Drying shrinkage	Less than 0.04% and is freeze thaw resistance



Products that meet the specific requirements of the harmonised standards EN771-5:2011 - manufactured stone masonry units, will be CE marked accordingly. Declarations of performance are available at www.forticrete-ce.com

For sales enquiries please contact our Anstone office on **01909 775000** Email us at **caststone@forticrete.com** or visit **www.forticrete.co.uk**

Forticretestone

