

# for millwork applications

Jack pine is an indigenous softwood species which is available in abundant volumes from Quebec. It slow growth and sound tight knot structure are such that it is highly suitable in knotty appearance applications. Jack pine has excellent machining and glueing properties. It texture and colour are such that it readily accepts all types of finishes.



Colour	Sapwo	Sapwood is nearly white in colour, the heartwood is often orange to light brown.			
Texture	Mediun	Medium and uneven. Grain generally straight.			
Common usage	No. 2 8	Premium: DIY market, panelling, joinery/millwork, fencing (wane free), patio (5/4), furniture  No. 2 & Better: Framing/Carcassing, flooring, industrial lumber, boards, doors, windows, bed frames  No. 3: Pallets, crating, packaging			
Carcassing	Jack Pine is also part of the SPF group for carcassing and structural application.		arcassing and structural application.		
Density	444 kg/m³ (volume air dry (12%), weight ovendry)				

## Machining properties in decreasing order of the overall performance of 17 species\*

Species	Planing good to excellent	Sanding excellent		multiple spur excellent	Mortising fair to excellent	Shaping fair to excellent	Turning fair to excellent	Average	
	(%)	(%)	(%)	(%)	(%)	(%)	(%)	(%)	ξ.
Red pine	83	68	96	80	78	72	96	82	1666-87
Yellow birch	89	52	98	86	56	78	100	80	
Eastern white cedar	71	94	100	68	56	60	98	78	are based on ASTM D
Sugar maple	69	82	98	100	38	56	100	78	0
Jack pine	57	84	94	76	62	58	94	75	7
Trembling aspen	74	4	98	66	98	86	96	75	000
Tamarack	49	84	98	64	66	82	72	74	2 5
White birch	70	8	98	88	66	74	100	72	٢
Black spruce	66	52	92	80	52	68	90	71	Toot
Eastern white pine	78	52	100	86	24	58	100	71	2
Red maple	63	40	92	98	42	50	100	69	7 5
Scots pine	66	40	96	80	36	70	94	69	7000
Norway spruce	66	74	96	56	70	58	50	67	
White spruce	67	52	92	50	44	74	62	63	1
Balsam fir	47	54	94	62	64	52	54	61	· Forintal
Sugi	91	66	96	54	24	60	30	60	
Eastern hemlock	36	72	94	56	18	66	6	50	2

<sup>\*</sup> Values are the pourcentage of tested specimens reaching the indicated performance.

### Regular Canadian Rough Green Sizes - Boards

•	<del>-</del>			
Nominal sizes (inches)	Net sizes (inches)	Net sizes (mm)		
1" x 3"	7/8" x 2 3/4"	22 mm x 70 mm		
1" x 4"	7/8" x 3 3/4"	22 mm x 95 mm		
5/4" x 3"	1 1/4" x 2 7/8"	32 mm x 73 mm		
5/4" x 4"	1 1/4" x 3 7/8"	32 mm x 98 mm		
5/4" x 5"	1 1/4" x 4 7/8"	32 mm x 123 mm		
5/4" x 6"	1 1/4" x 5 7/8"	32 mm x 149 mm		

<sup>\*</sup> Green rough sizes may vary from mills to mills and are available upon request

#### Canadian Kiln Dry Finish Sizes - Boards

Nominal sizes (inches)	Net sizes – D4S (inches)	Net sizes - D4S (mm)		
1" x 3"		19 mm x 64 mm		
1" x 4"	3/4" x 3 1/2"	19 mm x 89 mm		

#### Structural Dimensions for Rough Green Lumber

Nominal sizes (inches)	Net sizes (inches)	Net sizes (mm)
2" x 3"	1 11/16" x 2 3/4"	43 mm x 70 mm
2" x 4"	1 11/16" x 3 3/4"	43 mm x 95 mm
2" x 6"	1 11/16" x 5 3/4"	43 mm x 146 mm





979, avenue de Bourgogne Bureau 540 Québec (Québec) Canada G1W 2L4

**☎** (418) 650-6385 ☐ (418) 650-9011

info@quebecwoodexport.com www.quebecwoodexport.com