



## MIDI

### Small Format Solid Dense Blocks

**MIDI blocks are shorter format 140mm wide blocks to lower weight and enable safer repetitive manual handling. MIDI blocks are available in 'Standard' and 'Paint Grade' finishes.**

Three MIDI blocks laid with 10mm conventional mortar equates to two traditional 440mm long blocks.

All dense blocks are manufactured from high quality class 2 aggregates, including a significant proportion of recycled raw material and are suitable for use above and below damp-proof course (DPC).

MIDI dense blocks are manufactured to BS EN 771-3 and are ISO 9001 Quality Assured, ISO 14001 Environmentally Certified and hold BES 6001 Responsible Sourcing certification.

### TECHNICAL PROPERTIES

Property	Value
Face Size (BS EN 771-3):	290mm x 215mm
Dimensional Tolerance (BS EN 772-16):	Category D1
Gross Dry Density (BS EN 772-13):	1850 - 2100 kg/m <sup>3</sup>
Mean Compressive Strength (BS EN 772-1):	7.3, 10.4 N/mm <sup>2</sup> (Higher strengths are available to order)
Manufacturing Category (BS EN 771-3):	Category II
Thermal Conductivity (BS EN 1745):	1.17 W/mK [inner leaf] 1.26 W/mK [outer leaf]
Moisture Movement (BS EN 772-14):	< 0.6 mm/m
Fire Resistance (BS EN 13501-1):	Class A1 reaction to fire
Configuration (BS EN 1996-1-1):	Solid - Group 1
Available Texture, Finish:	Standard & Paint Grade



### APPLICATIONS

- Manufactured to BS EN 771-3.
- Inner & outer leaf of external cavity walls.
- Internal partition walls.
- Foundation walls below damp-proof course (DPC).
- Acoustic separating party walls to Part E of the Building Regulations and Robust Details.
- Standard texture finish provides an excellent surface for mortars, renders and plasters. Paint Grade finish available for smooth, internal painted applications.
- Robust, accepts most standard fixings.

### PHYSICAL PROPERTIES

Block Size mm	'R' Value m <sup>2</sup> k/W	Walled Weight kg/m <sup>2</sup> See Note 1	Sound Reduction Rw, dB See Note 2	Block Weight kg See Note 3	Fire Resistance Hours See Note 4
290 x 140 x 215	0.12	266	51	16.6	4

### PACK DETAILS

Block Size mm	Blocks per pack	m <sup>2</sup> per pack
290 x 140 x 215	72	4.8

1. Walled weight is for a single-leaf wall, plastered on both sides.
2. Sound Reduction Rw values are based on wall mass and assumes a plastered finish on both sides.
3. The block weights quoted above are approximate and include the typical additional weight from the equilibrium (3%) moisture content of the block. Received block weights will be significantly higher and are variable due to moisture content.
4. Fire resistance periods to BS EN 1996-1-2 for a single-leaf, non-loadbearing plastered wall.

Pack details may vary slightly between manufacturing locations. Always check details with your nearest sales office.

**Thermal**

The table below shows examples of how cavity walls built with a MIDI Dense block inner leaf can meet a range of u-value targets. For specific calculations, please contact our technical department.

U Value W/m²K	Partially Filled Cavity Brick outer leaf   50mm clear cavity   plasterboard on dabs	Fully Filled Cavity Brick outer leaf   Fully filled cavity   plasterboard on dabs
0.25	50mm PIR/PU @ 0.018 65mm PIR/PU @ 0.022	125mm batt @ 0.034
0.22	60mm PIR/PU @ 0.018 75mm PIR/PU @ 0.022	125mm batt @ 0.030
0.20	70mm PIR/PU @ 0.018 85mm PIR/PU @ 0.022	100mm batt @ 0.021
0.18	80mm PIR/PU @ 0.018 95mm PIR/PU @ 0.022	150mm batt @ 0.030
0.15	100mm PIR/PU @ 0.018 120mm PIR/PU @ 0.022	100mm batt @ 0.021 + 35mm insulated drylining

Note: Insulation thicknesses shown are the minimum required to meet the target u-value. These sizes may not be available, therefore the next size up should be used.

**Acoustic**

MIDI blocks are suitable for use in acoustic separating party walls between dwellings and for internal partitions in accordance with Part E of the Building Regulations. They are also suitable for a range of Robust Standard Detail party walls. The figures below are predicted sound reduction ratings based on wall mass:

Block Thickness mm	Walled Weight kg/m²	Predicted Sound Reduction, Rw		
		Unfinished	Plastered	Dry Lined
140	266	50	51	51

**Below Ground**

All of our aggregate and dense concrete blocks are durable products which are suitable for use in soil conditions up to Design Sulphate class DS-3 as defined in BRE Special Digest 1. MIDI dense Concrete blocks of any strength can be used below dpc.

**Suspended Block & Beam Floors**

MIDI blocks are not suitable for use as infill blocks in block and beam suspended floors.

**Fire Resistance**

Solid Dense blocks are non-combustible with zero spread of flame and are classed as Class 'A1' in accordance with BS EN 13501-1. Notional fire resistance periods based on BS EN 1996-1-2 are:

Block mm	Loadbearing Wall		Non-loadbearing Wall	
	No Finish	VG Plaster	No Finish	VG Plaster
140	3 hours	4 hours	4 hours	4 hours

"VG" = vermiculite / gypsum plaster or perlite plaster 13mm thick applied to both faces of single leaf walls.

NBS Clauses for our concrete block products can be found on [www.source.thenbs.com](http://www.source.thenbs.com)

**Mortars**

MIDI dense Standard blocks offer an excellent surface for accepting mortars and no pre-treatment is required other than ensuring that all dirt and debris is removed. Generally, in order to avoid unsightly cracking, the weakest mortar mixture appropriate to the structural requirements should be selected as per BS 5628-3. For most applications, we recommend that grade iii mortar is used.

	Mortar Class BS EN 1996-1-1	Recommended mix proportions of materials by volume (as per BS EN 998-2)	
Above dpc	(iii) M4	1 : 1 : 5½ to 6 1 : 5½ to 6 1 : 4½ to 5	Cement : Lime : Sand Cement : Sand (with plasticiser) Masonry Cement : Sand
Below dpc	(ii) M6	1 : ½ : 4 to 4½ 1 : 3½ to 4	Cement : Lime : Sand Cement : Sand

**External Rendering**

Standard-texture MIDI blocks have a surface which provides an excellent key for adhesion. These blocks have low - moderate suction and no special pre-treatment of the wall is required other than ensuring that all dirt and debris is removed from the surface. It is important that blocks are protected from the weather prior to and during rendering. Paint Grade MIDI blocks are not recommended for rendering due to their closer, smoother texture.

Traditional renders should be applied in 2 coats. The first coat should not exceed 15mm and the second coat 5 - 7mm. The first coat should be slightly stronger than the second coat. Render designation iii/M4 should be used, recommended proportions:

Cement : Lime : Sand With or without air entrainment	Cement : Sand With or without air entrainment	Masonry Cement : Sand With non-lime filler	Masonry Cement : Sand With lime filler
1 : 1 : 5 or 6	1 : 5 or 6	1 : 4 or 5	1 : 3½ to 4

**Wall Ties & Movement Joints**

Generally under normal conditions, wall ties should be embedded 50mm into the mortar on each leaf, staggered in alternate courses and spaced in accordance with the following:

Leaf Thickness mm	Cavity Width mm	Horizontal Spacing mm	Vertical Spacing mm	Ties per m²
Less than 90mm	50 - 75	450	450	4.9
Over 90mm	50 - 150	900	450	2.5

For unreinforced masonry panels, the typical recommended spacing between vertical movement joints for Dense blocks is 7m - 9m for internal and external walls.

**Good Site Practice & Safe Handling**

- Packs should be stored on firm, level ground no more than 2 packs high and protected from severe weather to preserve their quality. Care must be taken when removing the plastic bands as individual blocks may fall out. Never un-band packs above shoulder height.
- In the absence of a revised version of the HSE guidance given in their withdrawn Construction Sheet 37 ' Handling Building Blocks' the following principles should be followed: There is a risk of injury in the repetitive handling of blocks heavier than 20kg. Repetitive manual handling of blocks over 20kg should be subject to a risk assessment and a safe system of work should be established before block-laying commences.
- Blocks should not be laid if the temperature is at or below 3°C and falling.
- Blocks should always be laid on a full bed of mortar and vertical joints filled.



June 2023

Product details and availability may vary between manufacturing locations. Please contact your nearest regional sales office for sales, product and technical advice.

North East Region :	Tel: 01207 544 214	Fax: 01207 541 800	blocks@thomasarmstrong.co.uk
Cumbria, North Lancashire and Borders Region :	Tel: 01900 68114	Fax: 01900 66136	cumbriablocksales@thomasarmstrong.co.uk
Yorkshire, Humber and Lincolnshire Region :	Tel: 0113 232 0022	Fax: 0113 287 0839	leedssales@thomasarmstrong.co.uk
North West, Cheshire, Staffordshire and West Midlands Region :	Tel: 0151 525 5991	Fax: 0151 530 1676	aintreesales@thomasarmstrong.co.uk