

# EshaPUR 95/25 Oxidised Bitumen

## Product Data Sheet



A bituminous product manufactured by air blowing of penetration grade bitumen, at high temperature, resulting in a material of a much higher penetration index.

# EshaPUR

## 95/25 Oxidised Bitumen

### General Information

**EshaPur 95/25** is a hot applied oxidised bitumen solution for use on metal, concrete, stone or timber. 95/25 is a bituminous product manufactured by air blowing of penetration grade bitumen, at high temperature, resulting in a material of a much higher penetration index.

This product, utilised in the industrial sector, exhibits predominantly “solid” characteristics at ambient temperatures and provides excellent adhesive and waterproofing qualities when applied hot and allowed to cool.

The designation of the 95/25 refers to the mid point of the softening point acceptance criteria followed by the mid point of the penetration acceptance criteria (as can be seen in the specification below).

This material conforms to the requirement of the framework specification of BS EN 13304.

### Directions of Application

The roof area to be covered must be dry and clean, free from dust, dirt, grease or any other material, which may impair adhesion. Structural repairs should be made where necessary.

Prime absorbent surfaces with EshaPrimer in accordance with its application instructions. Allow primer to dry thoroughly before EshaPur is applied.

EshaPur should be broken into small lumps and put into a thermostatically controlled bitumen boiler a piece at a time, adding a piece at a time until there is sufficient molten adhesive for the work in hand and the bitumen attains its normal working temperature of 240°C. The use of a thermostatically controlled boiler helps minimise health and safety risks by ensuring the bitumen is not overheated. As with all bonding bitumen, do not heat above 260°C.

Traditional pour and roll methods for bonding built-up roofing should be used.

Only trained operatives should use hot bitumen. Always wear gloves and suitable personal protection equipment.

### PRODUCT SPECIFICATION

Essential characteristics	Performance	Test Method
Penetration @ 25°C (dmm)	20-30	EN1426
Softening Point (°C)	90-100	EN 1427
Solubility in Xylene (% min)	99	EN 12592
Loss on heating (% max)	0.5%	EN 13303
Flash Point (°C) min)	250	EN 22592

# EshaPUR

## 95/25 Oxidised Bitumen

### Recommendations for handling/ storage

Heating of packaged bitumen is a critical phase in most of the final uses. Typically, the packaged material is heated and melted in boilers out on site. However, control at the heating phase is very important in terms of health and safety as well as in maintaining the quality of the product.

Note must be taken of the maximum safe handling temperature of 230oC, this should not be abused. Bitumen is a poor conductor of heat, consequently, control of the heating phase is of paramount importance. The material should be broken up prior to placement in the boiler. This exposes a larger surface area to the heat and encourages a more even heating regime. Without the larger exposed surface area, aggressive heating at the base and sides of the boiler may well result in localised over heating, altering the characteristics of the keg and potentially causing thermal cracking of the bitumen, creating the release low flash vapours. The flash point of the keg then becomes irrelevant, as the fire risk is determined by these low flash vapours.

Melted bitumen should not be left in the boiler and reheated from cold, as there is then a high potential for localised overheating around the heating area (lack of convection means poor heat transfer) and potential development of a pressurised pocket of low flash vapours.

Be aware of the placement of any temperature monitoring or control devices. As a result of the poor thermal conductivity of the bitumen, a thermometer in the bitumen some distance from the heat source could read significantly different (even hundreds of degrees) from the true temperature of the bitumen near the heat source.

GRADE	GUIDE TO MINIMUM PUMPING – (@2000cP) TEMPERATURES (°C)	POURING TEMP (@ 200cP)		MAXIMUM SAFE HANDLING AND STORAGE TEMPERATURES (°C)
		TEMPERATURE °C	LITRES / TONNE	
95/25	170	205 - 215	1106	230

This information given in good faith and is based on the latest knowledge available to Radmat Building products Ltd. Whilst every effort has been made to ensure that the contents of the publication are current while going to press, customers are advised that products, techniques and codes of practice are under constant review and liable to change without notice.

For further information on Radmat products and services please call **01858 410372**, email [tech enquiries@radmat.com](mailto:tech enquiries@radmat.com) or visit our website [www.radmat.com](http://www.radmat.com)

**OCT 22**