

High Strength & Super Strength Grade


High Strength Grade and Super Strength Grade are used principally where higher compressive strengths are required such as in the foundations and lower storeys of three and four storey buildings, piers under high vertical loads and in multi-storey buildings.

Higher Strength grades are available in compressive strengths of 7.3N/mm² and 8.7N/mm² and in thicknesses from 100mm to 355mm (Super strength up to 150mm). They are third party accredited under BBA and certified for use in the applications listed.

Applications

- Internal and external leaf of cavity walls
- Solid walls
- Separating walls
- Flanking walls
- Partitions
- Multi-storey buildings
- Foundations
- Beam and shock floors





the positioning of the line may vary.



High Strength & Super Strength Grade

	High Strength Grade	Super Strength Grade
Compressive Strength	7.3N/mm ²	8.7N/mm ²
Thermal Conductivity	0.18 W/mK	0.18 W/mK
Density	730 kg/m³	730 kg/m³

	High Strength Grade* (black)	Super Strength Grade* (red)
Celcon Foundation Block 325 x 215mm		
Celcon Block - Scratch Marked 440 x 215mm		
Celcon Block - Plain Face 440 x 215mm		
Celcon Block Coursing Unit 215 x 65mm		
Celcon Plus Block - Plain Face 630 x 215mm		
Jumbo Bloks - Plain Face 630 x 250mm		



For further information and to check our most up-to-date product range, or to find your nearest stocking merchant, please visit our website www.hhcelcon.co.uk or contact the following departments:

Sales For sales enquiries or to find your local stockist please contact Tel: 01732 886444

Technical For technical enquiries please contact Tel: 01732 880580

H+H UK will always endeavour to reflect our product range and technical information as accurately as possible. We may however, need to update both from time to time during the life of this brochure. Please check with either our Sales or Technical departments to obtain the latest information prior to specification and purchase.



