

addaset[®]

Resin Bound Aggregate Surfacing

Permeable Driveways (SUDS)

Typical base build up

0.5mm dia grit cast onto uncured surface.

Surface Course

Hand applied and trowelled to a smooth finish by Addagrip approved installers.



The typical depth of Addaset resin bound paving surface.

6mm aggregate formulation requires a minimum of 18mm

10mm aggregate formulation requires a minimum of 24mm

Binder Course

Laid by others in well compacted layer.



A 70mm depth of AC 14 open surf asphalt concrete max 100/150 pen to BS EN 13108-1:2006. (Bituminous Macadam).

A geotextile membrane to prevent downward migration of fine soil particles (optional).

Sub-base

laid by others in well compacted layer.



A 175mm depth of well compacted Type 3 granular sub base to SHW clause 805 or 4/40mm, 4/20mm graded crushed concrete aggregate to EN12620 or locally available secondary or recycled aggregates which comply with the above specification blinded with 2/6.3mm graded crushed concrete aggregate to EN12620.

Impermeable membrane (optional).



Terram 900/1000/Advantage geotextile membrane to prevent upward migration of line soil particles (optional).

Capping Layer (if required)



Sub-grade



NOTE: A suitable steel, wood, brick, stone or aluminium edging should be provided to ensure a neat edge detail
Any advice, recommendation or information given by Addagrip Surface Treatments UK Limited is based on practical experience and is believed to be accurate at the time of publication, no liability or responsibility of any kind (including liability for negligence) is accepted in this respect by the company, its Servants, or Agents.

The figures quoted do not constitute a specification, they represent typical values obtained for this product.

