

TECHNICAL DATA SHEET

TDS: CVW4631B

ACRYLIC PRIMER SEALER UNDERCOAT

312/W463/1

DESCRIPTION:

Coo-Var Acrylic Primer Sealer Undercoat is a water based and low odour primer.

RECOMMENDED USE:

Coo-Var Acrylic Primer Sealer Undercoat is ideal for plaster preparation or any wood surface which requires priming inside or outside.

AVAILABILITY:

0.5 litre, 1 litre, 2.5 litre, 5 litre

FINISH:

Matt

COLOUR:

White

TYPICAL S.G. (SPECIFIC GRAVITY):

1.31 @ 20 °C

VOLUME SOLIDS:

32%

WET FILM THICKNESS W.F.T

75 microns

DRY FILM THICKNESS D.F.T

35 to 40 microns

EXPECTED SPREADING RATE:

13 sq.m / litre

@ 35 microns D.F.T

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

2.5 Poise @ 25 °C

FLASH POINT:

Non-flammable

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 30 mins @ 20 °C

Hard dry: 2 hours @ 20 °C

Full hardness: 5 to 7 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

6 hours @ 20 deg C

APPLICATION SPECIAL CONDITIONS:

N/A

VOC CONTENT:

Max 30 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application Do not apply below 7 °C.
restrictions

Method: Brush

Thinner Clean Water
(Max vol): (10%)

Nozzle size: N/A

Nozzle N/A
pressure:

Cleaning Water
solvent:

Recoat 6 hours @ 20
interval: deg C

SURFACE PREPARATION:

All surfaces should be clean, dry, sound and free from contaminants.

New wood should be sanded prior to coating to ensure an adequate "key" is produced.

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

Existing painted surfaces should be cleaned, degreased and sanded to ensure an adequate "key" is produced. Remove all loose, flaking material and treat bare areas as new substrate then prepare accordingly.

MIXING INSTRUCTIONS:

Mix well before use.

APPLICATION CONDITIONS:

Do not apply when temperature will be at 7°C or below. As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying.

PRECEDING COAT:

Apply direct

SUBSEQUENT COAT:

Suitable topcoat.

REMARKS:

Do not paint when temperature will be at 7°C or below during the painting and drying process.

HEALTH AND SAFETY:

See safety data sheet - SDS 10632

ISSUED:

25 October 2010

REVISION:

0

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 328053.

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

Ellenshaw Works
Lockwood Street, Hull HU2 0HN
Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR
Email: info@coo-var.co.uk
www.coo-var.co.uk