

*Economical, cement-based,  
dry-spray concrete*

# webercem conspray



## Uses

- Repairs to large areas of concrete
- Rock and embankment stabilisation
- General infilling
- Repairs of sea walls
- Spraying of mine shafts and tunnels
- Bridge abutment build-up
- Tunnel linings and masonry arches
- Diaphragm wall lining

## About this product

**webercem conspray** is a ready-to-use, cement-based concrete mix. It contains inert graded aggregates and dust suppressants. The formulation has been designed for dry process spray application to give rapid throughput, reduced rebound and to maximise application thickness.

Meets the requirements of BS EN 1504-3.

## Features and benefits

- ▲ Single component- ready to use
- ▲ Contains 5 mm inert coarse graded aggregate
- ▲ Fast throughput on large volume reinstatement jobs: over 5 tonnes per hour
- ▲ Economical – low rebound, less wastage of materials and labour (rebound levels of about 10% on vertical faces can be achieved by experienced nozzle operatives using well adjusted equipment)
- ▲ Safe to use and handle. Relatively low dust emission, no caustic accelerators
- ▲ High-build – up to 300 mm thickness can be applied in one pass on vertical faces
- ▲ Good adhesion to well prepared concrete
- ▲ Better ultimate strength than site-mixed gunite and many general purpose products

## Technical data

The values given below are indicative of typical properties that are achievable in good conditions by an experienced contractor. All the tests have been carried out on actual sprayed samples – not reconstituted mixes

### Physical properties

Dry density	2200 – 2300 kg/m <sup>3</sup>
Initial set	2 – 3 hours
Adhesion to concrete	> 2.0 N/mm <sup>2</sup>

# webercem conspray

## Preparation

As with all repairs and applications, it is essential to apply to a clean, sound surface free from all grease, oil, dust and loose material.

### Concrete

- Concrete substrates must be adequately prepared by a suitable mechanical method such as scabbing, grit blasting, water jetting or needle gunning, or by such other means as appropriate. Concrete must be carefully prepared to give a clean, freshly exposed surface. The outer limits of concrete patches should be cut square to avoid feather edges.
- Old concrete surfaces contaminated with oil or grease must be cleaned with a suitable detergent. Care must be taken to ensure that the oil or grease is removed from the surface and not simply spread over a larger area.
- In thicker sections, the engineer may require the sprayed concrete to be reinforced with mesh or bars. Reinforcing bars greater than 25 mm should be avoided. Mesh helps to evenly distribute stresses due to thermal movement or shrinkage and reduces the risk of cracking especially on corners. The mesh should be fixed in accordance with the recommendations in Concrete Society Technical Report No 15.
- In some cases, additional mesh reinforcement may not be required by the Engineer.
- Soak the concrete surface thoroughly, allowing surplus water to drain off.

### Steel

- Steel substrates including exposed reinforcement should be free of loose rust and grease. Ideally they should be grit blasted to a uniform grey metal finish to achieve first quality to BS7079: Part A1 followed by degreasing with a suitable solvent immediately prior to bonding.
- Any formwork or extra reinforcement such as steel mesh should be designed / prepared and fixed in accordance with the guidelines of the Code of Practice (see below).

## Application

Guidelines on the method of working are detailed in the Code of Practice for Sprayed Concrete published by the Concrete Society and should be strictly observed.

**webercem conspray** should be emptied from the bags directly into the hopper of the dry process spraying machine. The equipment should be balanced so as to produce a steady stream of material with minimal pulsing. The amount of water added at the spraying nozzle will be controlled by the nozzle man - too low an addition will increase rebound and dust emission; too wet a mix will slump. The correct amount of water can be judged by the appearance of the sprayed concrete; any glossiness of the surface should be avoided.

In case of a long delay between applied coats of the sprayed concrete, the surface of the newly applied hardened concrete should be water jetted using a maximum air pressure and water flow through the nozzle to ensure that any laitance and all weak or loose material has been removed. The surface should be allowed to drain before proceeding with the next coat.

**webercem conspray** can be applied down to 20 mm thickness, but the recommended minimum thickness for protection over steel is 40 mm.

## Finishing

Any necessary trowelling or profiling should be done immediately after spraying has finished. An 'as sprayed' appearance is recommended, but, if overcoating is to follow, finish with a wooden float or damp sponge.

## Curing

**webercem conspray** must be properly cured if it is to achieve its optimum properties. Cure immediately with a high efficiency curing membrane unless the surface is to be overcoated or subject to chemical impregnation, in which case cure with polythene sheeting and/or wet hessian for a minimum of 3 days.

**Protect from frost.**

## Packaging

**webercem conspray** is packed in 25 kg paper sacks.

## Yield

Approximately 11 litres per 25 kg bag, but an allowance must be made for rebound and profiling.

## Storage and shelf life

When stored airtight in a dry place at temperatures above 5°C and protected from frost, shelf life is 12 months from date of manufacture.

## Health and safety

Contains cement (Contains chromium (VI). May produce an allergic reaction). Harmful by inhalation. Irritating to eyes and skin. Keep out of the reach of children. In case of contact with eyes, rinse immediately with plenty of water and seek medical help. After contact with skin, wash immediately with plenty of soap and water. Wear suitable protective clothing, gloves and eye/face protection.

**For further information, please request the Material Safety Data Sheet for this product.**

### Technical services

Weber's Customer Services Department has a team of experienced advisors available to provide on-site advice both at the specification stage and during application. Detailed specifications can be provided for specific projects or more general works. Site visits and on-site demonstrations can be arranged on request.

#### Technical helpline

Tel: 08703 330 070  
e-mail: technical@netweber.co.uk

### Sales enquiries

Weber products are distributed throughout the UK through selected stockists and distributors. Please contact the relevant Customer Services Team below for all product orders and enquiries.

#### UK and Ireland

Tel: 08703 330 070  
Fax: 0800 014 2995  
e-mail: customerservice@netweber.co.uk

### Saint-Gobain Weber

Dickens House, Enterprise Way, Maulden Road, Flitwick, Bedford MK45 5BY, UK  
Tel: 08703 330 070 Fax: 0800 014 2995 e-mail: mail@netweber.co.uk  
www.netweber.co.uk

To the best of our knowledge and belief, this information is true and accurate, but as conditions of use and any labour involved are beyond our control, the end user must satisfy himself by prior testing that the product is suitable for his specific application, and no responsibility can be accepted, or any warranty given by our Representatives, Agents or Distributors. Products are sold subject to our Standard Conditions of Sale and the end user should ensure that he has consulted our latest literature.