

THE ULTIMATE FILLER

TX[®]110 RAPID DRYING FILLER



- ▶ **EXCEPTIONAL ADHERENCE**
- ▶ **EXCELLENT SHAPING QUALITIES**
- ▶ **NO NEED TO SPOT PRIME**
- ▶ **WILL NOT FLASH OR GRIN**
- ▶ **CAN BE PAINTED IN 3 HRS**

PURPOSE

Rapid drying filler, for interior use, in powder, manual application.

SUBSTRATES

TX[®]110 applies on new or renovated, painted or unpainted Substrates :

- Gypsum plaster, plaster tiles, plaster boards
- Old painted surfaces
- Cement, concrete, cellular concrete, breeze blocks, bricks, stones
- Primed wood

OVERCOATING

TX[®]110 can be coated with any filler, any conventional paint or conventional wall-coating. Do not cover straight with polyurethane or solvent-based epoxy paints. If using a solvent based paint, a first primer coat of waterborne masonry paint is highly recommended.

Physical and technical FEATURES

TX[®]110: exterior filler in powder, made of cement , selected quarry material and resin.

- Characterization (NFT 36-005) : Family III - Class 3
- Codification (EN 16-566) : G₃S₂V₀W₀A₀C₀R₀
- Mixing rate: 45% water (hence .45 l water for 1 kg powder)
- Application thickness : not limited
- Consumption: 1 kg powder fills 1 l
- Working time : 30 to 40 minutes
- Second coat: when the filler is touch dry and sandable
- Painted/overcoated: in 3 hrs average time (time relevant to a thickness coat of 1 cm)
- Colour: extra white
- Shore hardness: 80
- Adherence filler-substrate: (EN 16-566): >0.5 MP

USE AND STORAGE CONDITIONS

- Application tools : coating knife, blade or trowel.
- Tools cleaning : with water.
- Preservation: product guaranteed 12 months, from the original purchase invoice date as evidence, in its original sealed packaging and stored away from humidity.

PACKAGING

- Box of 2 kg, Bag in bag of 5 and of 10 kg

RECOMMENDATIONS and care for use

- Do not apply **TX[®]110** on polystyrene or on wall paper or any bonded coverings. Do not apply on exterior substrates.
- Do not apply: under a temperature below 8°C nor above 35°C nor at an hygrometry rate above 70%.
- Do not apply on overheated surfaces.
- Do not apply on damp surfaces or when condensation conditions are likely to occur.
- Do not further mix the paste once it has begun to set.

SUBSTRATES PREPARATION

- Substrates to be prepared as per the current trade practices.
- Substrates must be hard, cohesive, clean, sound and dry.

NORMATIVE DOCUMENTS to be referred to

- EN 16-566: Coating Fillers for interior and/or exterior works.
- NFT 36-005: Characterization of paint products.
- DTU 59.1 (NFP 74-201): Building paint works.
- DTU 59.4 (NFP 74-204) : Wall papers and wall coatings works.

HEALTH AND SAFETY


- Contains cement – please read the care for use guidelines on the packaging or on the MSDS before handling.
- Safety data sheets available on www.toupret.co.uk

The data sheet information, especially the guidelines relevant to the application and final use of **TX[®]110** are provided in good faith and result from the knowledge of the products and experience of TOUPRET Company.

The product is required to be used as per the trade practices rules book and in reference to our recommendations.

The information provided is relevant to applications processed under a temperature of 20°C, a hygrometry rate of 50 % and on normal-absorbent substrates.

The times mentioned are only indicative and depend on the substrate, the coat thickness, and the ambient conditions



Information on the level of emission of volatile substances in indoor air, presenting a risk of inhalation toxicity, on a class scale from A + (very low emissions) to C (high emissions).