

**[READY
TO USE]**

PULSAR LEVELLING SPRAY SKIMMING FILLER BY AIRLESS MACHINE



- ▶ **CAN BE SPRAYED, TROWELLED, ROLLERED**
- ▶ **IDEAL FOR TAPING AND JOINTING**
- ▶ **ADHERES TO PAINTED SURFACES**
- ▶ **HIGH BUILD FINISH : UP TO 5 MM**
- ▶ **MAY BE APPLIED MANUALLY**

PURPOSE

Skimming filler in paste form. Interior use, for either manual or machine application.

SUBSTRATE

PULSAR can be applied on either new or renovated substrates, either unpainted or painted:

- Gypsum plaster, plasterboards/drywall lining
- Old painted surfaces
- Any **TOUPRET** fillers
- Cement, concrete, cellular concrete, breeze blocks, bricks, stones
- Fibreglass cloth, structured surfaces

OVERCOATING

PULSAR can be coated over by any type of **TOUPRET** fillers, any conventional paints and wall coverings.

Physical and technical FEATURES

PULSAR: is a filler in paste form for interior use, made of selected mineral components and resin.

- Characterization (NFT 36-005): Family III - Class 2
- Codification (EN 16-566): $G_3S_2V_0W_0A_0C_0R_0$
- Application thickness: up to 5 mms
- Consumption: 1.7 kg/m²/mm
- Second coat: once the filler is dry
- Overcoat: 24 to 48 HRS average time (once completely dry)
- Colour: white
- Adhesion filler/substrate (EN 16-566): > 0.5 Mpa

USE AND STORAGE CONDITIONS

- Application tools:
 - Manual Application: coating blade or roller
 - Machine application: any type of Airless piston machine with minimum flow of 5L/minFor optimum use, we recommend the following nozzles: 5.31, 5.35, 6.31 or 6.35.
- Tools cleaning: with water
- Preservation: product guaranteed 12 months, from the original purchase invoice date as evidence, in its original sealed packaging and stored away from frost and sun.

PACKAGING

- Bucket of 20 kg.

RECOMMENDATIONS

and care for use

- Do not apply **PULSAR** on polystyrene, nor on adhesive coverings, nor on exterior substrates.
- Do not apply under a temperature < 8 °C and > 35 °C nor under an hygrometry rate over 70%.
- Do not apply on warm/overheated surfaces nor under sun exposure.
- Do not apply on damp substrates.

SUBSTRATES PREPARATION

- Substrates to be prepared as per the current trade practices.
- Substrates must be hard, cohesive, clean, sound and dry.

NORMATIVE DOCUMENTS

to be referred to

- EN 16-566: Coating fillers for interior works and/or exterior .
- NFT 36-005: Characterization of paint products.
- French DTU 59.1 (NFP 74-201): Building paint works.
- French DTU 42.1 (NFP 84-404): wall papers and wall coverings processing

HEALTH AND SAFETY

- No danger tag.
- Safety data sheets available on www.toupret.co.uk

The data sheet information, especially the guidelines relevant to the application and final use of **PULSAR** are provided in good faith and result from the knowledge of the products and experience of **TOUPRET** company.

The product is required to be used as per the trade practices rules book and in reference to our recommendations.

The information provided is relevant to applications processed under a temperature of 20°C, a hygrometry rate of 50 % and on normal-absorbent substrates.

The times mentioned are only indicative and depend on the substrate, the coat thickness, and the ambient conditions.