

**TROWEL
OR SPRAY**

AIRSPRAY 2 IN 1

**LEVELLING AND SKIMCOATING
BY AIRLESS MACHINE**

- ▶ **READY TO USE**
- ▶ **VERY SMOOTH**
- ▶ **EASY TO SAND**
- ▶ **FINE & WHITE**
- ▶ **EASY TO TROWEL**
- ▶ **MAY BE APPLIED MANUALLY**



PURPOSE

Levelling filler in paste form for Airless spraying/trowel for interior use.

SUBSTRATES

AIRSPRAY 2 IN 1 can be applied on either unpainted or painted substrates:

- Gypsum plaster; plasterboards/drywall lining
- Honeycomb concrete, breeze blocks, cellular concrete, bricks, cement
- Old painted surfaces
- Fibreglass cloth, old textured surfaces (i.e Artex)
- Limewash mortar

OVERCOATING

AIRSPRAY 2 IN 1 can be coated over by any conventional paints, any type of filler and wall coverings.

Physical and technical FEATURES

AIRSPRAY 2 IN 1: filler in paste form for interior use, made of calcium carbonates loads and resins

- Characterization (NFT 36-005): Family III-Class 2
- Codification (EN 16566): $G_3S_1V_0W_0A_0C_0R_0$
- Application thickness: up to 5 mm
- Consumption: 1.7 kg/m²/mm
- Second coat: once the filler is dry
- Overcoat: 24 to 48 HRS average time (once completely dry)
- Colour: white
- White index: 60
- Shore hardness: 80
- Adhesion filler/substrate (EN 16566): > 0.5 Mpa

USE AND STORAGE CONDITIONS

- Application tool : any type of Airless piston machine with minimum flow of 5L/min. For optimum use, we recommend the following nozzles: 5.31, 5.35, 6.31 or 6.35.
- Tools cleaning: with water
- Preservation: product guaranteed 12 months, from the original purchase invoice date as evidence, in its original sealed packaging and stored away from frost and sun.

PACKAGING

- Bucket of 25 kg

RECOMMENDATIONS

and care for use

- Do not apply under a temperature < 8 °C and > 35 °C nor under an hygrometry rate over 70%.
- Do not apply on overheated surfaces
- Do not apply on damp substrates
- Do not apply on polystyrene, nor on wall paper, nor on exterior substrates.

SUBSTRATES PREPARATION

- Substrates to be prepared as per the current trade practices.
- Substrates must be hard, cohesive, clean, sound and dry.

NORMATIVE DOCUMENTS

to be referred to

- EN 16566: Coating Fillers for interior and/or exterior works.
- NFT 36-005: Characterization of paint products.
- DTU 59.1 (NFP 74-201): Building paint works.
- DTU 59.4 (NFP 74-204): wall papers and wall coverings processing

HEALTH AND SAFETY

- No danger tag.
- Very low VOC emissions : <0.02%
- Safety data sheets available on www.toupret.co.uk

The data sheet information, especially the guidelines relevant to the application and final use of **AIRSPRAY 2 IN 1** are provided in good faith and result from the knowledge of the products and experience of TOUPRET Company.

The product is required to be used as per the trade practices rules book and in reference to our recommendations.

The information provided is relevant to applications processed under a temperature of 20°C, a hygrometry rate of 50 % and on normal-absorbent substrates.

The times mentioned are only indicative and depend on the substrate, the coat thickness, and the ambient conditions



Information on the level of emission of volatile substances in indoor air, presenting a risk of inhalation toxicity, on a class scale from A+ (very low emissions) to C (high emissions).