

HUMISTOP

ANTI-DAMP TREATMENT

[**STOPS**
DAMPNESS]



- ▶ **COVERS MICRO-CRACKS**
- ▶ **FLEXIBLE FILM**
- ▶ **APPLY BY BRUSH, ROLLER OR SPRAYING**
- ▶ **WATERBORNE**
- ▶ **WHITE**

PURPOSE

Ideal for the treatment of damp walls before painting or wall papering. Prevents paint flaking or wall paper disbonding. Manual application interior or exterior.

SUBSTRATES

HUMISTOP can be applied on damp but not dripping substrates :

- Old painted substrated
- Cement
- Brick
- Stone
- Wet surfaces

OVERCOATING

HUMISTOP can be overcoated by any type of current paint or coating.

Physical and technical FEATURES

HUMISTOP: is a water based filler, for exterior and interior use, made of mineral and synthetic binder.

- Characterization (NFT 36-005): Family I class 7b2
- Directive 2004/42/CE : category A/a (VOCs 2010) : maximum 15 g/L
- Consumption: about 3 m²/L for 2 coats.
- Colour : white
- Second coat: 8 hours average time
- Overcoating: average 24 hours

USE AND STORAGE CONDITIONS

- Application tools : brush or roller.
- Application : in two cross coats.
- Tools cleaning: with water.
- Preservation: product guaranteed 12 months, from the original purchase invoice date as evidence, in its original sealed packaging and stored away from humidity.

PACKAGING

- Tin of 1 kg

RECOMMENDATIONS and care for use

- Do not apply under a temperature of 8°C internally and 5°C externally, over 70 % HR (hygrometry rate) internally and 80 % HR externally.
- Do not apply on overheated or frozen surfaces, under conditions that could speed drying or when condensation conditions are likely to occur (hot bright sunlight for instance).
- Do not use to protect horizontal surfaces (terraces, pools...) against water.
- **HUMISTOP** is not a waterproof filler.

SUBSTRATES PREPARATION

- Substrates to be prepared as per the current trade practices.
- Substrates must be hard, cohesive, clean and sound.

NORMATIVE DOCUMENTS to be referred to

- NFT 36-005: Characterization of paint products.
- French DTU 59.1 (NFP 74-201): Building paint works.
- French DTU 59.4 (NFP 74-204): Setting up of wall papers and wall coatings.
- French DTU 42.1 (NFP 84-404): façades renovation with polymer-based waterproofing coatings.

HEALTH AND SAFETY

- Low VOC emissions : < 0,5 %
- Safety data sheets available on www.toupret.co.uk

The data sheet information, especially the guidelines relevant to the application and final use of **HUMISTOP** are provided in good faith and result from the knowledge of the products and experience of TOUPRET Company.

The product is required to be used as per the trade practices rules book and in reference to our recommendations.

The information provided is relevant to applications processed under a temperature of 20°C, a hygrometry rate of 50 % and on normal-absorbent substrates.

The times mentioned are only indicative and depend on the substrate, the coat thickness, and the ambient conditions



Information on the level of emission of volatile substances in indoor air, presenting a risk of inhalation toxicity, on a class scale from A+ (very low emissions) to C (high emissions).