

TECHNICAL DATA SHEET – HPC 52 NU-STEEL SP ANTI CORROSIVE PRIMER/UNDERCOAT

DESCRIPTION:

Nu-Steel SP Anti Corrosive Primer / Undercoat is a high performance phosphate primer and undercoat.

ADVANTAGES:

Provides first class adhesion to properly prepared surfaces.

USES:

First coat of the Nu-Steel SP System.

COLOUR RANGE:

Available in Grey and Red Oxide.

PACK SIZE:

Single component product, supplied in 5 litre units.

VOLUME SOLIDS:

55%

COVERAGE RATE:

8-10 m² / Litre

DRYING TIME:

Touch: 2 Hours
Overcoat: 4 Hours.

PREPARATION:

Ensure surfaces to be treated are clean, free from contamination and dry. Previously coated surfaces should be abraded

APPLICATION:

By brush/roller or spray.

EQUIPMENT CARE:

All equipment should be cleaned with T2 Thinners

STORAGE:

Store away from direct sunlight and sources of heat. Protect from frost.

SHELF LIFE:

12 months (in original sealed container).

HEALTH & SAFETY:

Refer to MSDS